



INNOVATIONS FOR LIVING®

Metal Building Utility Blanket

Product Data Sheet



Physical Properties

Property	Test Method	Value
Noncombustible	CAN/ULC S114	Meets Max temp rise, no flaming and max mass loss criteria
Nominal Density	ASTM C 167	0.8 PCF
Fire Hazard Classification	ASTM E 84, UL 723, CAN/ULC S102	FHC 25/50
Moisture Absorption	ASTM C 1104	<2% by weight
Fungi Resistance	ASTM C 1338	No growth greater than comparative item

¹The surface burning characteristics of these products have been determined in accordance with ASTM E 84, UL 723, or CAN/ULC S102. These standards should be used to measure and describe the properties of materials, products or assemblies in response to heat and flame under controlled laboratory conditions and should not be used to describe or appraise the fire hazard or fire risk of materials, products or assemblies under actual fire conditions. However, results of this test may be used as elements of a fire risk assessment which takes into account all of the factors which are pertinent to an assessment of the fire hazard of a particular end use. Values are reported to the nearest 5 rating.

Description and Uses

Owens Corning Metal Building Utility Blanket is an unfaced light density fibrous glass blanket. The product is designed to be laminated with a variety of facings and is used for condensation and noise control in metal buildings. The product is available in rolls with widths of 36", 48" and 72" at a nominal product thickness of 2".

Application

After the product is laminated with an appropriate facing, the insulation is typically installed in a single layer between the structural members (purlins for roofs and girts for walls) and the exterior panels. In most cases, the product is installed over and perpendicular to the structural members with the facing towards the interior of the structure. Care should be taken not to

Thermal Resistance

Thickness		R-Value	RSI Value
Inches	mm		
2	51	7.0 ¹	1.23 ¹

¹Pre-lamination values

overstretch the insulation material as excess compression can reduce the insulation's thermal performance. All seams should be sealed to help maintain a continuous vapor retarder.

Metal Building Utility Blanket can also be used over the purlins in roof systems that utilize a primary layer of insulation between the purlins.

Availability

Owens Corning Metal Building Utility Blanket is fabricated and distributed by a nationwide network of independent

laminators assuring prompt service and delivery. Contact your Owens Corning sales representative for the names of insulation laminators servicing your area.

Specification Compliance

CAN/ULC - S702 - Standard for Mineral Fiber Thermal Insulation for Buildings-Type I.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.



OWENS CORNING INSULATING SYSTEMS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1-800-GET-PINK™
www.owenscorning.com



Pub. No. 45109-C. Printed in U.S.A. February 2009. The GREENGUARD Indoor Air Quality Certified is a certification mark used under license through the GREENGUARD Environmental Institute. THE PINK PANTHER™ & ©1964-2009 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. ©2009 Owens Corning.